

FORM PTO-1390 (REV 10-94)		U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE	ATTORNEYS DOCKET NUMBER
TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371			01-488
INTERNATIONAL APPLICATION NO. PCT/EP00/00648		INTERNATIONAL FILING DATE January 28, 2000	U.S. APPLICATION NO. (if known, see 37 CFR 1.13) 09/890923
TITLE OF INVENTION MOULDED ARTICLE		PRIORITY DATE CLAIMED February 17, 1999	
APPLICANT(S) FOR DO/EO/US By Martin Hintermann			
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:			
<p>1. <input checked="" type="checkbox"/> This is a FIRST submission of items concerning a filing under 35 U.S.C. 371.</p> <p>2. <input type="checkbox"/> This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371.</p> <p>3. <input checked="" type="checkbox"/> This express request to begin national examination procedures (35 U.S.C. 371(h)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).</p> <p>4. <input checked="" type="checkbox"/> A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.</p> <p>5. <input checked="" type="checkbox"/> A copy of the International Application as filed (35 U.S.C. 371(c)(2))</p> <p style="margin-left: 20px;">a. <input checked="" type="checkbox"/> is transmitted herewith (required only if not transmitted by the International Bureau).</p> <p style="margin-left: 20px;">b. <input type="checkbox"/> has been transmitted by the International Bureau.</p> <p style="margin-left: 20px;">c. <input type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US)</p> <p>6. <input checked="" type="checkbox"/> A translation of the International Application into English (35 U.S.C. 371(c)(2)).</p> <p>7. <input type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))</p> <p style="margin-left: 20px;">a. <input type="checkbox"/> are transmitted herewith (required only if not transmitted by the International Bureau).</p> <p style="margin-left: 20px;">b. <input type="checkbox"/> have been transmitted by the International Bureau.</p> <p style="margin-left: 20px;">c. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired.</p> <p style="margin-left: 20px;">d. <input type="checkbox"/> have not been made and will not be made.</p> <p>8. <input type="checkbox"/> A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).</p> <p>9. <input checked="" type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).</p> <p>10. <input checked="" type="checkbox"/> A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)). (Amended Pages 1-5a)</p> <p>Items 11. to 16. below concern document(s) or information included:</p> <p>11. <input type="checkbox"/> An Information Disclosure Statement under 37 CFR 1.97 and 1.98.</p> <p>12. <input checked="" type="checkbox"/> An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.</p> <p>13. <input type="checkbox"/> A FIRST preliminary amendment.</p> <p style="margin-left: 20px;"><input type="checkbox"/> A SECOND or SUBSEQUENT preliminary amendment.</p> <p>14. <input type="checkbox"/> A substitute specification.</p> <p>15. <input type="checkbox"/> A change of power of attorney and/or address letter.</p> <p>16. <input type="checkbox"/> Other items or information:</p>			

Page 1 of 2

Express Mail No.:
EL394335919US

I hereby certify that this correspondence is being
deposited with the United States Postal Service as
Express Mail in an envelope addressed to: Commissioner
of Patents and Trademarks, Washington, D.C. 20231

on August 7, 2001

(Date of Deposit)
Rachel Piscitelli

Name and Reg. No. of Attorney

Signature

August 7, 2001

Date of Signature

(January 1995)

7 AUG 1964

Form PTO-1390 (REV 10-94) page 2 of 2

I hereby certify that this correspondence is being deposited with the United States Postal Service as Express Mail in an envelope addressed to: Commissioner of Patents and Trademarks, Washington, D.C. 20231

on August 7, 2001

(Date of Deposit)
Rachel Piscitelli

Name and Reg. No. of Attorney
Rachael Fissant
Signature
August 7 2007
Date of Signature

09/890923

J003 Rec'd PCT/PTO 07 AUG 2001

PCT/EP00/00648 (as amended)

Moulded Article

The present invention concerns fibre-reinforced moulded articles made of a textile planar formation as a woven fabric of at least two fibre materials, means and a process for their production and use.

It is known to produce preforms e.g. from glass-fibre-reinforced thermoplasts. For this a thermoplastic moulding compound and glass fibre matting are processed in a pressing process into a fibre laminate material. This process is suitable mainly for the production of plate-like semi-finished products. The disadvantage is that substantially only smooth planar or plate-like structures can be produced. Structured moulded articles or components cannot be produced or only indirectly produced by way of the smooth planar plate-like structures in an additional moulding step.

EP 630 735 discloses hybrid yarn which can be processed into textile planar formations of two thermoplastic fibre materials. In one pressing process the textile planar formation is transferred to a fibre-reinforced plastic part, where a first fibre material preferably present as staple fibres is melted under the effect of pressure and heat and transforms into a matrix-forming material, while a second stretchable fibre material preferably present as endless fibres remains in the plastic part as a reinforcement material.

EP 835 741 describes the production of a premould which contains a reinforcement material in the form of rovings of staple fibres, where the fibres of the rovings have at most a slight twist in relation to each other. The preform of aligned or unaligned rovings is impregnated with a matrix material and processed into fibre-reinforced plastic parts.

EP 302 989 describes a woven fabric made from yarn for

09/890923-EP00648

production of fibre-reinforced plastic parts. The woven fabric contains different yarns of a first and second material. The yarns of a first material consist of a matrix-forming material and, under the effect of pressure and heat in production of the plastic part, transform into a matrix structure. The yarns of the second material constitute the fibre reinforcement in the plastic part.

The task of the present invention is to avoid these disadvantages and in particular create moulded articles and a process for their production which, starting from a fibre material, leads to moulded articles or components in one working process and in short processing times.

According to the invention this is achieved in that the woven fabric is made of a hybrid yarn of staple fibres and the staple fibres of the hybrid yarn are made of a first material or materials and a second material or materials, and the moulded article contains a matrix which is the re-set product of staple fibres brought to a plastic state of at least one thermoplastic first material and contains, embedded in the matrix, aligned fibres in the form of staple fibres of at least one second material, and the staple fibres of the second material are inorganic fibres, where a softening, melt or decomposition point of the staple fibres of the second material lies above the softening or melt point of the first material, and where the fibre orientation of the second material in the matrix corresponds to the fibre orientation of the textile planar formation.

The textile planar formations can be aligned fibres in uni-directional layers, bi-directional layers, as cut rovings, woven, knitted or laid fabrics.

Suitably, the staple fabrics of the first material have a mean length of 10 to 150 mm, suitably 30 to 120 mm, preferably 60 to 100 mm and in particular 75 to 85 mm.

Suitably, the staple fibres of the second material have a mean length of 10 to 150 mm, suitably 30 to 120 mm, preferably 60 to 100 mm and in particular 75 to 85 mm.

In particular, the textile planar formations contain staple fibres of the first and second material each with a mean length of 75 to 85 mm.

The staple fibres of the first thermoplastic material can for example contain or consist of polyamide, polyester, polycarbonate, polyurethane, polyurea, polyolefins, polystyrenes, polyacrylnitrile, polyvinyl chloride, polyvinylidene chloride, polyvinyl alcohol or polytetrafluoroethylene. Staple fibres of polyamide are preferred, such as polyamide 6, polyamide 6.6, polyamide 11 or in particular polyamide 12.

The staple fibres of the second material are for example high-temperature-resistant inorganic or organic fibres. For example, organic staple fibres can contain or consist of fully aromatic polyamides, aramides, heterocyclene-containing aromatic polyamides, polyimides, polyimidamides, polybenzimidazoles, polyoxdiazoles, polytriazoles, polythiadiazoles, polybenzoxazoles, polychinazolidines, poly-bis-benzimidazole-benzophenanthroline or chelated polyterephthaloyl-oxalamidrazone. Further examples are inorganic staple fibres which suitably contain or consist of glass, slag, stone, ceramic, quartz, silica glass, boron, silicon carbide, boron nitride, boron carbide, aluminium oxide, zirconium oxide, steel, aluminium, tungsten, carbon or graphite or can be a monocrystalline corundum or monocrystalline silicon carbide. Staple fibres are preferable made of glass, carbon or graphite. Other examples are staple fibres of natural substances which suitably consist of or contain cotton, wool, silk, or fibres of jute, sisal, coir, linen or hemp.

To control the properties, the staple fibres of

098093-09070
T04090-22605850

thermoplastic material and in particular the staple fibres of organic material of the second material can contain fire-inhibiting additives, pigments, colourings, fillers etc.

The temperature range of the softening, melt or decomposition point of the staple fibres of the second material is suitably selected such that this lies at least 5%, suitably 10% and in particular 30% above the softening or melt point of the first material.

In moulded articles according to the present invention, the staple fibres of the second material are formed as aligned fibres in uni-directional layers, bi-directional layers, as cut rovings, woven, knitted or laid fabrics embedded in the matrix which is the re-set product of staple fibres transferred to a plastic state of the thermoplastic first material. The fibre orientation of the original textile planar formation remains stretched. The textile planar formation of aligned fibres in uni-directional layers, in bi-directional layers, the cut rovings, woven, knitted or laid fabrics can be used in one or more layers, e.g. 1, 2, 3, 4, 5 layers etc. according to the required final thickness and strength of the moulded article. Stretching of for example up to 20% can advantageously be achieved in 1-layer textile planar formations whereas stretching of up to 35% and more is advantageously achieved with multi-layer, for example 4-layer, textile planar formations. The textile planar formations can for example have a density of 100 to 1000 g/m².

In the present moulded article the staple fibres of the second material in relation to the volume account for 40 to 70%, suitably 50 to 60% and preferably 53 to 59%, and accordingly the matrix of the thermoplastic first material in relation to volume accounts for 60 to 30%, suitably 50 to 40% and preferably 47 to 41%.

The present invention also comprises textile planar

formations of aligned fibres in uni-directional layers, bi-directional layers, as cut rovings, woven, knitted or laid fabrics of a mixture of staple fibres of at least two materials, where the staple fibres of at least one thermoplastic first material are present in proportions of 60 to 30% in relation to volume and the staple fibres of at least one second material are present in proportions of 40 to 70% in relation to volume, for production of the moulded article according to the invention. The staple fibres are in a hybrid yarn or a mixed yarn of the first material or materials and the second material or materials. The hybrid yarn of staple fibres is processed into a woven fabric. The woven fabric can have a weave of 1-1, 1-2, 1-3, 1-4, 1-5 etc. I.e. the weft threads can lie alternatively over or under 1, 2, 3, 4, 5 etc. warp threads. The fibre orientation can for example be 0°/90°. Particularly preferred is a satin 4-1 weave. The textile planar formations can be used in 1, 2, 3, 4 or 5 layers, where fabrics with 1, 2, 3, 4 or 5 layer fabrics are preferred. Depending on the final thickness of the moulded article a higher number of layers can be used or within a moulded article the number of layers can vary. For example, heavily stressed areas on the finished moulding can be made thicker by a multiplicity of layers, whereas less stressed areas can be constructed by one or more fewer layers. For two or more layers, the fibre orientation of the individual layers can be the same or twisted and/or offset in relation to each other.

The textile planar formations can be used in 1, 2, 3, 4 or 5 layers, where fabrics with 1, 2, 3, 4 or 5 layer fabrics are preferred. Depending on the final thickness of the moulded article a higher number of layers can be used or within a moulded article the number of layers can vary. For example, heavily stressed areas on the finished moulding can be made thicker by a multiplicity of layers, whereas less stressed areas can be constructed by one or more fewer layers. For two or more layers, the fibre orientation of the individual layers can be the same or twisted and/or offset in relation

0980923-080701

to each other.

The aligned fibres in uni-directional layers, bi-directional layers, as cut rovings, woven, knitted or laid fabrics, and in particular the staple fibres of a second material can on their surface be fitted with adhesion promotion agents such as adhesion size, plastic size e.g. PA 6.6 size etc. The aligned fibres in uni-directional layers, bi-directional layers, as cut rovings, woven, knitted or laid fabrics of a mixture of staple fibres of at least two materials can be subjected to a drying process before moulding where drying can be performed at high temperature, for example temperatures in a range of 60 to 100°C and/or in vacuum, preferably at 100 to 500 mbar.

The moulded articles according to the invention formed from textile planar formations with aligned fibres as woven fabrics from at least two fibre materials can be produced in that the woven fabric is made of a mixture of staple fibres of at least two materials, where the woven fabric is made of a hybrid yarn of staple fibres and the staple fibres of the hybrid yarn are made of a first material or materials and of a second material or materials, and the staple fibres of at least one thermoplastic first material account for 60 to 30% in relation to volume and those of at least one second material of inorganic fibres account for 40 to 70% in relation to volume, said fabric is preheated until the first material softens or melts and is then placed in a tool and deformed into the moulded article under pressure application for shaping at constant high temperature of the tool and die which lies in a range below the softening or melt temperatures of the first material.

The pressing process takes place in a tool or female mould and under pressure application by means of a die or male mould for shaping and at temperatures of the die and tool below the

softening or melt temperatures of the first material. This process is also known as the cold stamping process.

Preheating can take place by radiation such as IR radiation, by convection etc. The preheating temperature depends on the melt temperature of the first material and is above the melt point of the first material and below a softening, melt or decomposition point of the second material. For example, for a polyamide 12 as a first material a preheating temperature of up to 250°C can be used. The textile planar formation can for example be heated by radiation when placed on or tensioned in a frame, or by contact heating when lying on a heat source. In the latter case adhesion of the first material to the heated surface must be prevented. In preheating the temperature of the textile planar formation must be raised to plastic deformation or melting of the first material. The preheated textile planar formation with the softened or melted first material is plastically deformed at least so far that its fibre structure disappears and a matrix forms, where the staple fibres of the second material retain their fibre structure and orientation embedded in the matrix. In other words consolidation takes place. The preheated textile planar formation is then passed to the next processing step.

The mould can for example be a tool, swage or female mould. The staple fibres can be laid in or on the tool, also known as the swage or female mould, as consolidated preheated textile planar formations in the form of aligned fibres in uni-directional layers, bi-directional layers, cut rovings, woven, knitted or laid fabrics of a mixture of staple fibres, and be subjected to pressure by means of a rigid or elastic die also known as a male mould. Deformation can be carried out at a substantially constant high temperature of the tool or tool and die. The temperature of the tool or tool and die preferably lies slightly below the softening or melt temperature of the first material. The residual heat from the preheated textile planar formation or matrix

Under the pressure the textile planar formations of aligned fibres in uni-directional layers, bi-directional layers as cut rovings, woven, knitted or laid fabrics, deform according to the negative form of the tool and die. Preferably, isostatic pressing occurs. Advantageously, the isostatic pressing takes place by means of a resilient rubber die. Thus, for example, moulded articles can be formed with a base and oblique or vertical side walls or for multi-part tools undercuttings can be produced. The deformation can take place on the principle of deep drawing i.e. deformation by drawing the material while the material thickness remains the same, stretch-forming i.e. by establishing the material along its side edges by means of a retainer and stretching the material with thickness reduction, a combination of stretch-forming and deep drawing i.e. only partial drawing of the material to be deformed, or by vacuum forming. Stretch-forming is preferred. On stretching during stretch-forming or combined stretch-forming and deep-drawing, the staple fibres of the second material - held in the matrix formed of the first material - undergoes an extension with simultaneous reduction in thickness. The individual fibres or fibrils which form the staple fibres are substantially surrounded by the plastic or

melted thermoplastic first material and, supported by a resulting fibre slip effect, in a fibre slip process the staple fibres are elongated under thickness reduction.

For deep drawing and/or stretch-forming, for example a drawing ratio Ω of 1 to 3, preferably 1.2 to 2.1 and in particular 1.8 to 2.0 can be applied. The drawing ratio Ω is the quotient of the applied length a to the stretched length b. The drawing ratio thus follows the formula $\Omega = a/b$. The applied length a corresponds to the actual wall length of the moulded article, the stretched length b corresponds to the length of projection of the moulded article.

The tool or female mould can be heated. For easy extraction from the mould, at least the deformation-active surface is made of chrome, chrome steel, nickel, teflon, nickel-teflon etc. The metal surfaces are suitably smooth and in particular polished or lapped. For easy extraction from the mould after the pressing process, release and/or anti-adhesion agents can be applied.

At least the deformation-active parts of a resilient rubber male mould or die are for example made of silicon rubber. The male mould or die can also be heatable.

The temperature for deformation of the consolidated material laid between tool and die depends on the softening or melt temperature of the first material. The temperature for deformation and consolidation preferably lies below the melt point and in particular below the crystallisation temperature of the first material. For example for polyamides, and preferably polyamide 12, temperatures of 70°C to 160°C are suitable, where temperatures of 110°C to 150°C are advantageous.

The application pressures are for example 25 to 100 bar, suitably 40 to 60 bar and in particular 50 bar. The thickness of the moulded article according to the invention

05850523-080701

can be selected according to the thickness of the textile planar formation and the number of jointly pressed layers. Typical thicknesses of moulded articles are for example 0.5 to 5 mm. The thickness can vary within a moulded article. The moulded articles can for example be profile-like structured parts or plate-like parts (e.g. organo-panels) etc.

The moulded articles according to the present invention can be used in vehicles for water, road or rail or on stationary constructions. Examples of such parts are doors, hoods, side parts, front and rear skirts, bumpers, trims, bulkheads, reinforcements or holders on vehicle bodies; panels, walls, bulkheads, floors, ceilings or parts thereof on buses or rail vehicles; trims, bulkheads etc. in ships; trims, bulkheads, partition walls, floor or ceiling elements on outer facades or in the interior of stationary constructions such as buildings etc. Preferred applications are doors, hoods, side parts, front and rear skirts, bumpers, floor assemblies and roofs or parts thereof for cars and trucks.

Example:

1. A fibre matting with a density of 500 g/cm² of 4 layers of a satin 4-1 weave with a 0°/90° fibre orientation of staple fibre hybrid yarn, substantially 44 vol% polyamide staple fibre and 56 vol% carbon staple fibre with a mean length of 80 mm, is placed on a frame and heated by IR radiation within 75 seconds to approximately 220°C and held at this temperature for approximately 10 seconds for consolidation. The polyamide staple fibres here lose their structure and form a matrix surrounding the carbon fibres. This preheated intermediate product is laid on the tool heated to approximately 150°C, established at the edges with a retainer, and the die with the resilient rubber shaping surface is lowered into the tool. The closing time of the press is around 3 seconds, the pressure applied 50 bar and the retention time under pressure in the press 5 seconds. In

104080" E366860

the pressing process the intermediate product of the fibre matting deforms plastically. The required contours of the moulded article are formed from the matrix by the negative form of the tool and by the die. The carbon fibres stretch or elongate during the pressing process due to the fibre slip effect under reduction of thickness according to the deformation depth of the tool. The negative form of the tool offers a tapered recess. The intermediate product of the fibre matting is pressed by the die into the recess where the staple fibres of the second material according to their position in the tapered recess extend by up to 35% of their original length. The original fibre orientation of the woven fabric is retained. After the pressure of the die is relieved, the finished moulded article can be taken from the tool, and where applicable treated by deburring and/or other processes such as painting, coating with foil or similar. The thickness of the moulded article is approximately 1.5 mm.

TO 030 826 058 01

CLAIMS

1. Fibre-reinforced moulded article made of a textile planar formation, characterised in that the moulded article contains a matrix which is the re-set product of staple fibres brought to a plastic state of at least one thermoplastic first material, and contains embedded in the matrix aligned fibres in the form of staple fibres of at least one second material, where the softening, melt or decomposition point of the staple fibres of the second material lies above the softening or melt point of the first material, and where the fibre orientation of the second material in the matrix corresponds to the fibre orientation of the textile planar formation.
2. Moulded article according to claim 1, characterised in that the staple fibres of the first material have a mean length of 10 to 150 mm, suitably 30 to 120 mm, preferably 60 to 100 mm and in particular 75 to 85 mm.
3. Moulded article according to claim 1, characterised in that the staple fibres of the second material have a mean length of 10 to 150 mm, suitably 30 to 120 mm, preferably 60 to 100 mm and in particular 75 to 85 mm.
4. Moulded article according to claim 1, characterised in that the staple fibres of the first thermoplastic material contain or consist of polyamide, preferably polyamide 12, polyester, polycarbonate, polyurethane, polyurea, polyolefins, polystyrenes, polyacrylnitrile, polyvinyl chloride, polyvinylidene chloride, polyvinyl alcohol or polytetrafluoroethylene.
5. Moulded article according to claim 1, characterised in that the second material contains or consists of high-temperature-resistant organic staple fibres suitably fully aromatic polyamides, aramides, heterocyclene-

containing aromatic polyamides, polyimides, polyimidamides, polybenzimidazoles, polyoxdiazoles, polytriazoles, polythiadiazoles, polybenzoxazoles, polychinazolidines, poly-bis-benzimidazole-benzophenanthroline or chelated polyterephthaloyl-oxalamidrazone, inorganic staple fibres suitably of glass, slag, stone, ceramic, quartz, silica glass, boron, silicon carbide, boron nitride, boron carbide, aluminium oxide, zirconium oxide, steel, aluminium, tungsten, preferably carbon, graphite or a monocrystalline corundum and silicon carbide, or natural fibres preferably cotton, wool, silk, jute, sisal, coir, linen or hemp.

6. Moulded article according to claim 1, characterised in that the temperature range of the softening, melt or decomposition point of the staple fibres of the second material lies at least 5%, suitably 10% and in particular 30% above the softening or melt point of the first material.
7. Moulded article according to claim 1, characterised in that in the moulded article the staple fibres of the second material, formed as uni-directional layers, bi-directional layers, cut rovings, laid, interlaced, woven or knitted fabrics, are embedded in the matrix which is the re-set product of staple fibres brought to a plastic state of the thermoplastic first material.
8. Moulded article according to claim 1, characterised in that in the moulded article the staple fibres of the second material in relation to the volume account for 40 to 70%, suitably 50 to 60% and preferably 53 to 59%, and correspondingly the matrix of the thermoplastic first material in relation to the volume accounts for 60 to 30%, suitably 50 to 40% and preferably 47 to 41%.
9. Moulded article according to claim 1, characterised in

09990923-080701

that the moulded article is the matrix of the thermoplastic first material or materials which contains embedded in the matrix the aligned fibres in the form of staple fibres of the second material or materials, where the fibre orientation of the second material in the matrix corresponds to the fibre orientation of the textile planar formation and the staple fibres of the second material or materials in the matrix are made thinner by stretching than in the textile planar formation.

10. Textile planar formation of aligned fibres in uni-directional layers, bi-directional layers, as cut rovings, laid, woven or knitted fabrics of a mixture of staple fibres of at least two materials, where the staple fibres of at least one thermoplastic first material account for 60 to 30% in relation to volume and the staple fibres of at least one second material account for 40 to 70% in relation to volume, for production of moulded articles according to claim 1.
11. Process for production of moulded articles made from textile planar formations according to claim 1, characterised in that the textile planar formation of aligned fibres in uni-directional layers, bi-directional layers, as cut rovings, laid, woven or knitted fabrics of a mixture of staple fibres of at least two materials, where the staple fibres of at least one thermoplastic first material account for 60 to 30% in relation to the volume and the staple fibres of at least one second material account for 40 to 70% in relation to the volume, is preheated until the first material softens or is melted and is then brought into a tool and deformed into the moulded article under pressure application for forming at constant high temperature of the tool and die which lies in a range below the softening or melt point of the first material.

0989092-080704
T02080-22605860

12. Process for production of moulded articles according to claim 11, characterised in that the preheated textile planar formation is placed in a tool and is deformed into the moulded article under pressure application for forming at a constant high temperature of the tool and die which lies in a range below the softening or melt point of the first material, under stretching and thickness reduction of the staple fibres of the second material while retaining the fibre orientation of the textile material.
13. Process for production of moulded articles according to claim 11, characterised in that the pressure application for moulding is isostatic.
14. Vehicles for water, road or rail or parts thereof, stationary constructions or parts thereof, using moulded articles according to claim 1.

TO 090 22606850

DECLARATION AND POWER OF ATTORNEY

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name,

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

MOULDED ARTICLE

Case No. 01-488, the specification of which

(check one)

_____ is attached hereto.

_____ was filed on January 28, 2000 as
PCT Application Serial No. PCT/EP00/00648
and was amended on _____
(if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, §1.56(a) and understand that information is material where there is substantial likelihood that a reasonable examiner would consider it important in deciding whether to allow the application to issue as a patent.

I do not know and do not believe this invention was ever known or used in the United States of America before my or our invention thereof, or patented or described in any printed publication in any country before my or our invention thereof or more than one year prior to this application, that the same was not in public use or on sale in the United States of America more than one year prior to this application, that the invention has not been patented or made the subject of an inventor's certificate issued before the date of this application in any country foreign to the United States of America on an application filed by me or my legal representatives or assigns more than twelve months prior to this application, and that no application for patent or inventor's certificate on this invention has been filed in any country foreign to the United States of America prior to this application by me or my legal representatives or assigns, except as identified below:

I hereby claim foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) for patent or inventor's certificate listed below

Prior Foreign Application(s)

Number	Country	Date
<u>300/99</u>	<u>SWITZERLAND</u>	<u>FEB. 17, 1999</u>
_____	_____	_____
_____	_____	_____

and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the above listed application on which priority is claimed:

Prior Foreign Application(s)

Number	Country	Date
_____	_____	_____
_____	_____	_____
_____	_____	_____
_____	_____	_____
_____	_____	_____
_____	_____	_____

If no priority is claimed, I have identified all foreign patent applications filed prior to this application:

Prior Foreign Application(s)

Number	Country	Date
_____	_____	_____
_____	_____	_____
_____	_____	_____
_____	_____	_____
_____	_____	_____
_____	_____	_____

And I hereby appoint Robert H. Bachman (19,374), Gregory P. LaPointe (28,395), Richard S. Strickler (18,228), and Barry L. Kelmacher (29,999), all members of the firm of Bachman & LaPointe, P.C., A Professional Corporation.


Gregory P. LaPointe
Telephone: 203-777-6628

my attorneys with full power of substitution and revocation, to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith and direct that all correspondence be forwarded to:

Bachman & LaPointe, P.C.
Suite 1201
900 Chapel Street
New Haven, CT 06510-2802

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full name of sole or first inventor MARTIN HINTERMANN

Inventor's signature  Date July 31, 2001

Residence Arbonerstrasse 9, CH-9315 Neukirch, Switzerland
Citizenship Swiss
Post Office Address same as above